

This page is mainly introduced the 1J46 Datasheet, including chemical information,mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of 1J46, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Datasheet for Steel Grades Special Alloy 1J46

	1J46 Standard Number:				
ITEM	ITEM Standard Number Descriptions				

1J46 Chemical composition(mass fraction)(wt.%)										
Chemical Min.(%)						Max.(%)				
С	Si	Mn	Р	S	Cr	Ni	M	0	V	Та
0.03	0.15-0.30	0.60-1.10	0.020	0.020		45.0-46	.5			
W	N	Cu	Co	Pb	В	Nb	А	I	Ti	Other
		≤0.2								

1J46

1J46 Physical Properties					
Tensile strength	115-234	σb/MPa			
Yield Strength	23	σ 0.2 ≥/MPa			
Elongation	65	δ5≥ (%)			
Ψ	-	ψ≥ (%)			
Akv	-	Akv≥/J			
HBS	123-321	-			
HRC	30	-			

1J	1J46 Mechanical Properties				
Tensile strength	231-231	σb/MPa			
Yield Strength	154	σ 0.2 ≥/MPa			
Elongation	56	δ5≥(%)			



Steel Grades1J46 Chemical information, Mechanical properties

Physical properties, Mechanical properties, Heat treatment, and Micro structure

Ψ	-	ψ≥(%)
Akv	-	Akv≥/J
HBS	235-268	-
HRC	30	-

1J46 Heat Treatment Regime						
Annealing Quenching		Tempering	Normalizing	Q & T		
V	√	√	V	√		

1J46 Range of products						
Product type	Products	Dimension	Processes	Deliver Status		
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting		
Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,		
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot- Rolled	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting		
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID- WASHED		

We can produce Special Alloy the specifications follows: