

This page is mainly introduced the STS316Ti Datasheet, including chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of STS316Ti, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Datasheet for Steel Grades Special Alloy STS316Ti

STS316Ti Standard Number:

ITEM	Standard Number	Descriptions
------	-----------------	--------------

STS316Ti Chemical composition (mass fraction) (wt.%)

Chemical			Min. (%)				Max. (%)		
C	Si	Mn	P	S	Cr	Ni	Mo	V	Ta
Max 0.08	Max 1.00	Max 2.00	Max 0.045	Max 0.03	16.0-18.0	10.00-14.0	2.00-3.00		
W	N	Cu	Co	Pb	B	Nb	Al	Ti	Other
								5xC _□	

KS standard austenite stainless steel bars (KS D3706-1992)

STS316Ti Physical Properties

Tensile strength	115-234	σ_b /MPa
Yield Strength	23	$\sigma_{0.2} \geq$ /MPa
Elongation	65	$\delta_5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	Akv \geq /J
HBS	123-321	-
HRC	30	-

STS316Ti Mechanical Properties

Tensile strength	231-231	σ_b /MPa

Yield Strength	154	$\sigma_{0.2} \geq / \text{MPa}$
Elongation	56	$\delta_5 \geq (\%)$
ψ	-	$\psi \geq (\%)$
Akv	-	$Akv \geq / \text{J}$
HBS	235-268	-
HRC	30	-

STS316Ti Heat Treatment Regime

Annealing	Quenching	Tempering	Normalizing	Q & T
√	√	√	√	√

STS316Ti Range of products

Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar, Square Bar	$\Phi 8$ -1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil / Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot-Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-WASHED

We can produce Special Alloy the specifications follows: