

This page is mainly introduced the 18MnCr11XS Datasheet, including chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of 18MnCr11XS, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

## Datasheet for Steel Grades Structure Steel 18MnCr11XS

18MnCr11XS Standard Number:					
ITEM	ITEM Standard Number Descriptions				
TIEM	Standard Number	Descriptions			

18MnCr11XS Chemical composition(mass fraction)(wt.%)									
Chemical Min.(%) Max.(%)									
С	Si	Mn	Р	S	Cr	Ni	Мо	V	Та
0.15-0.21	0.17-0.37	0.90-1.20	0.025	0.020-0.0 35	0.90-1.20	0.3	0.15		
W	N	Cu	Со	Pb	В	Nb	Al	Ti	Other
		0.30						0.02	

## 18MnCr11XS

18MnCr11XS Physical Properties					
Tensile strength	115-234	σb/MPa			
Yield Strength	23	σ 0.2 ≥/MPa			
Elongation	65	δ5≥ (%)			
ψ	-	ψ≥ (%)			
Akv	-	Akv≥/J			
HBS	123-321	-			
HRC	30	-			

18MnCr11XS Mechanical Properties					
Tensile strength	231-231	σb/MPa			



Yield Strength	154	σ 0.2 ≥/MPa
Elongation	56	δ5≥(%)
ψ	-	ψ≥(%)
Akv	-	Akv≥/J
HBS	235-268	-
HRC	30	-

18MnCr11XS Heat Treatment Regime						
Annealing Quenching Tempering Normalizing Q & T						
	$\checkmark$	$\checkmark$	$\checkmark$	$\checkmark$		

18MnCr11XS Range of products							
Product type	Products	Dimension	Processes	Deliver Status			
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting			
Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,			
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot- Rolled	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting			
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID- WASHED			

## We can produce Structure Steel the specifications follows: