

This page is mainly introduced the Q390GNH Datasheet, including chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of Q390GNH, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

## Datasheet for Steel Grades Structure Steel Q390GNH

### Q390GNH Standard Number:

ITEM	Standard Number	Descriptions
------	-----------------	--------------

### Q390GNH Chemical composition (mass fraction) (wt.%)

Chemical			Min.(%)				Max.(%)			
C	Si	Mn	P	S	Cr	Ni	Mo	V	Ta	
Max 0.12	0.15-0.65	Max 1.40		0.035						
W	N	Cu	Co	Pb	B	Nb	Al	Ti	Other	
		0.25-0.55						Max 0.10	RE Max 0.12	

### Q390GNH

### Q390GNH Physical Properties

Tensile strength	115-234	$\sigma_b$ /MPa
Yield Strength	23	$\sigma_{0.2} \geq$ /MPa
Elongation	65	$\delta_{5\geq}$ (%)
$\psi$	-	$\psi \geq$ (%)
Akv	-	Akv $\geq$ /J
HBS	123-321	-
HRC	30	-

### Q390GNH Mechanical Properties

Tensile strength	231-231	$\sigma_b$ /MPa

Yield Strength	154	$\sigma_{0.2} \geq / \text{MPa}$
Elongation	56	$\delta_5 \geq (\%)$
$\psi$	-	$\psi \geq (\%)$
Akv	-	$Akv \geq / \text{J}$
HBS	235-268	-
HRC	30	-

### Q390GNH Heat Treatment Regime

Annealing	Quenching	Tempering	Normalizing	Q & T
√	√	√	√	√

### Q390GNH Range of products

Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar, Square Bar	$\Phi 8$ -1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil / Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot-Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-WASHED

**We can produce Structure Steel the specifications follows:**