

This page is mainly introduced the S20C Datasheet, including chemical information,mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of S20C, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

## **Datasheet for Steel Grades Structure Steel S20C**

	S20C Standard Number:				
ITEM	Standard Number	Descriptions			

S20C Chemical composition(mass fraction)(wt.%)										
	Chemical Min.(%) Max.(%)									
С	Si	Mn	Р	S	Cr	Ni		Мо	V	Та
0.18-0.23	0.15-0.35	0.30-0.60	0.025	0.035	0.20					
W	N	Cu	Co	Pb	В	Nb		Al	Ti	Other
	0.20	0.30								

## **S20C**

S20C Physical Properties					
Tensile strength	115-234	σb/MPa			
Yield Strength	23	σ 0.2 ≥/MPa			
Elongation	65	δ5≥ (%)			
Ψ	-	ψ≥ (%)			
Akv	-	Akv≥/J			
HBS	123-321	-			
HRC	30	-			

S2	S20C Mechanical Properties				
Tensile strength	231-231	σb/MPa			
Yield Strength	154	σ 0.2 ≥/MPa			
Elongation	56	δ5≥(%)			



## Steel GradesS20C Chemical information, Mechanical properties

Physical properties, Mechanical properties, Heat treatment, and Micro structure

Ψ	-	ψ≥(%)
Akv	-	Akv≥/J
HBS	235-268	-
HRC	30	-

S20C Heat Treatment Regime							
Annealing	Annealing Quenching Tempering Normalizing Q & T						
√	V	√	√	√			

S20C Range of products						
Product type	Products	Dimension	Processes	Deliver Status		
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting		
Steel Bar	Round Bar, Flat Bar, Square Bar	Ф8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,		
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot- Rolled	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting		
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID- WASHED		

## We can produce Structure Steel the specifications follows: