

This page is mainly introduced the SKH50 Datasheet, including chemical information,mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of SKH50, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Datasheet for Steel Grades Tool Steel And Hard Alloy SKH50

	SKH50 Standard Number:					
ITEM	ITEM Standard Number Descriptions					

SKH50 Chemical composition(mass fraction)(wt.%)									
	Chemical			Min.(%)			Max.(%)		
С	Si	Mn	Р	S	Cr	Ni	Мо	V	Ta
0.77-0.87	Max 0.70	Max 0.45			3.50-4.50		8.00-9.00	1.00-1.40	
W	N	Cu	Co	Pb	В	Nb	Al	Ti	Other
1.40-2.00									

SKH50

SKH50 Physical Properties					
Tensile strength	115-234	σb/MPa			
Yield Strength	23	σ 0.2 ≥/MPa			
Elongation	65	δ5≥ (%)			
Ψ	-	ψ≥ (%)			
Akv	-	Akv≥/J			
HBS	123-321	-			
HRC	30	-			

SKI	es		
Tensile strength	231-231	σb/MPa	
Yield Strength	154	σ 0.2 ≥/MPa	



Steel GradesSKH50 Chemical information, Mechanical properties

Physical properties, Mechanical properties, Heat treatment, and Micro structure

Elongation	56	δ5≥(%)
Ψ	-	ψ≥(%)
Akv	-	Akv≥/J
HBS	235-268	-
HRC	30	-

SKH50 Heat Treatment Regime						
Annealing Quenching Tempering Normalizing Q & T						
√	√	√	√	√		

SKH50 Range of products							
Product type	Products	Dimension	Processes	Deliver Status			
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting			
Steel Bar	Round Bar, Flat Bar, Square Bar	Ф8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,			
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot- Rolled	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting			
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID- WASHED			

We can produce Tool Steel And Hard Alloy the specifications follows: