

This page is mainly introduced the 8Cr3 Datasheet, including chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of 8Cr3, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

## Datasheet for Steel Grades Tool Steel And Hard Alloy 8Cr3

8Cr3 Standard Number:						
ITEM Standard Number	Descriptions					

8Cr3 Chemical composition(mass fraction)(wt.%)									
Chemical				Min.(%)			Max.(%)		
С	Si	Mn	Р	S	Cr	Ni	Мо	V	Та
0.75[]0.85	≤0.40	≤0.40	≤0.030	≤0.030	3.20[]3.80				
W	N	Cu	Со	Pb	В	Nb	Al	Ti	Other

8Cr3 Physical Properties							
Tensile strength	115-234	σb/MPa					
Yield Strength	23	σ 0.2 ≥/MPa					
Elongation	65	δ5≥ (%)					



Ψ	-	ψ≥ (%)
Akv	-	Akv≥/J
HBS	123-321	-
HRC	30	-

## 8Cr3 Mechanical Properties

Tensile strength	231-231	σb/MPa	
Yield Strength	154	σ 0.2 ≥/MPa	
Elongation	56	δ5≥(%)	
Ψ	-	ψ≥(%)	
Akv	-	Akv≥/J	
HBS	235-268	-	
HRC	30	-	

8Cr3 Heat Treatment Regime						
Annealing Quenching		Tempering	Normalizing	Q & T		
$\checkmark$	$\checkmark$	$\checkmark$	$\checkmark$	$\checkmark$		

8Cr3 Range of products						
Product type	Products	Dimension	Processes	Deliver Status		
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting		
Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,		
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot- Rolled	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting		
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID- WASHED		

## We can produce Tool Steel And Hard Alloy the specifications follows: