

This page is mainly introduced the 1.4006 Datasheet, including chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of 1.4006, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Datasheet for Steel Grades Specialsteel 1.4006

| 1.4006 Standard Number: | | |
|-------------------------|-----------------------|--|
| ITEM | Standard Number | Descriptions |
| 1 | DIN 1654-5 (1989) | Cold heading and cold extruding steels; technical delivery conditions for stainless steels |
| 2 | DIN 17440 (1996) | Stainless steels - Technical delivery conditions for drawn wire |
| 3 | DIN 17441 (1985) | Stainless steels - Technical delivery conditions for cold rolled strips and slit coils strip and sheets cut from such strips for pressure purposes |
| 4 | DIN 17456 (1985) | Seamless circular tubes of stainless steels for general requirements; technical delivery conditions |
| 5 | DIN EN 10088-3 | Stainless steels - Part 3: Technical delivery conditions for semi-finished products, bars, rods, wire, sections and bright products of corrosion resisting steels for general purposes |
| 6 | DIN EN 10088-4 | Stainless steels - Part 4: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for construction purposes |
| 7 | DIN EN 10088-5 | Stainless steels - Part 5: Technical delivery conditions for bars, rods, wire, sections and bright products of corrosion resisting steels for construction purposes |
| 8 | DIN EN 10250-4 | Open die steel forgings for general engineering purposes - Part 4: Stainless steels |
| 9 | DIN EN 10263-5 | Steel rod, bars and steel wire for cold heading and cold extrusion - Part 5: Technical delivery conditions for stainless steels |
| 10 | DIN EN 10272 | Stainless steel bars for pressure purposes |
| 11 | DIN EN 10297-2 (2005) | Seamless circular steel tubes for mechanical and general engineering purposes - Technical delivery conditions - Part 2: Stainless steel |
| 12 | DIN EN 10088-1 | Stainless steels - Part 1: List of stainless steels |
| 13 | DIN EN 10088-2 | Stainless steels - Part 2: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for general purposes |

| 1.4006 Chemical composition(mass fraction)(wt.%) | | |
|--|---------|---------|
| Chemical | Min.(%) | Max.(%) |
| C | 0.08 | 0.15 |
| Si | | 1.00 |
| Mn | | 1.50 |
| P | | 0.040 |

| | | | | | | | | | | |
|----|----|----|------|----|----|----|------|----|-------|--|
| S | | | 0.15 | | | | 0.35 | | | |
| Cr | | | 12.0 | | | | 13.0 | | | |
| Ni | | | | | | | 0.60 | | | |
| C | Si | Mn | P | S | Cr | Ni | Mo | V | Ta | |
| W | N | Cu | Co | Pb | B | Nb | Al | Ti | Other | |
| | | | | | | | | | | |

Steel FE-PM1901 (X12CrNi13) - 600 MPa ≤ Rm ≤ 800 MPa - Bars - De ≤ 70 mm

Stainless steels - Technical delivery conditions for drawn wire

Stainless steels - Part 1: List of stainless steels

Ferritic stainless steel

1.4006 Physical Properties

| | | |
|------------------|---------|-------------------------|
| Tensile strength | 115-234 | σ _b /MPa |
| Yield Strength | 23 | σ _{0.2} ≥ /MPa |
| Elongation | 65 | δ ₅ ≥ (%) |
| ψ | - | ψ ≥ (%) |
| Akv | - | Akv ≥ /J |
| HBS | 123-321 | - |
| HRC | 30 | - |

1.4006 Mechanical Properties

| | | |
|------------------|---------|-------------------------|
| Tensile strength | 231-231 | σ _b /MPa |
| Yield Strength | 154 | σ _{0.2} ≥ /MPa |
| Elongation | 56 | δ ₅ ≥ (%) |
| ψ | - | ψ ≥ (%) |
| Akv | - | Akv ≥ /J |
| HBS | 235-268 | - |
| HRC | 30 | - |

| 1.4006 Heat Treatment Regime | | | | |
|------------------------------|-----------|-----------|-------------|-------|
| Annealing | Quenching | Tempering | Normalizing | Q & T |
| √ | √ | √ | √ | √ |

| 1.4006 Range of products | | | | |
|--------------------------|--|----------------------------|---|---|
| Product type | Products | Dimension | Processes | Deliver Status |
| Plates / Sheets | Plates / Sheets | 0.08-200mm(T)*W*L | Forging, hot rolling and cold rolling | Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting |
| Steel Bar | Round Bar, Flat Bar, Square Bar | Φ8-1200mm*L | Forging, hot rolling and cold rolling, Cast | Black, Rough Turning, Shot Blasting, |
| Coil / Strip | Steel Coil /Steel Strip | 0.03-16.0x1200mm | Cold-Rolled & Hot-Rolled | Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting |
| Pipes / Tubes | Seamless Pipes/Tubes, Welded Pipes/Tubes | OD:6-219mm x WT:0.5-20.0mm | Hot extrusion, Cold Drawn, Welded | Annealed, Solution and Aging, Q+T, ACID-WASHED |

We can produce Specialsteel the specifications follows: