

This page is mainly introduced the 1.4028 Datasheet, including chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of 1.4028, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Datasheet for Steel Grades Specialsteel 1.4028

1.4028 Standard Number:		
ITEM	Standard Number	Descriptions
1	DIN 17440 (1996)	Stainless steels - Technical delivery conditions for drawn wire
2	DIN 17441 (1985)	Stainless steels - Technical delivery conditions for cold rolled strips and slit coils strip and sheets cut from such strips for pressure purposes
3	DIN EN 10088-2	Stainless steels - Part 2: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for general purposes
4	DIN EN 10088-3	Stainless steels - Part 3: Technical delivery conditions for semi-finished products, bars, rods, wire, sections and bright products of corrosion resisting steels for general purposes
5	DIN EN 10088-1	Stainless steels - Part 1: List of stainless steels
6	DIN EN 10151	Stainless steel strip for springs - Technical delivery conditions
7	DIN EN 10250-4	Open die steel forgings for general engineering purposes - Part 4: Stainless steels

1.4028 Chemical composition (mass fraction) (wt.%)									
Chemical		Min.(%)				Max.(%)			
C		0.26				0.35			
Si						1.00			
Mn						1.50			
P						0.045			
S						0.015			
Cr		12.0				14.0			
C	Si	Mn	P	S	Cr	Ni	Mo	V	Ta
W	N	Cu	Co	Pb	B	Nb	Al	Ti	Other

Stainless steels - Technical delivery conditions for cold rolled strips and slit coils strip and sheets cut from such strips for pressure purposes

1.4028 Physical Properties

Tensile strength	115-234	σ_b /MPa
Yield Strength	23	$\sigma_{0.2} \geq$ /MPa
Elongation	65	$\delta 5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	Akv \geq /J
HBS	123-321	-
HRC	30	-

1.4028 Mechanical Properties

Tensile strength	231-231	σ_b /MPa
Yield Strength	154	$\sigma_{0.2} \geq$ /MPa
Elongation	56	$\delta 5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	Akv \geq /J
HBS	235-268	-
HRC	30	-

1.4028 Heat Treatment Regime

Annealing	Quenching	Tempering	Normalizing	Q & T
√	√	√	√	√

1.4028 Range of products

Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot-Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-

				WASHED
--	--	--	--	--------

We can produce Specialsteel the specifications follows: