

This page is mainly introduced the NCF 800 Datasheet, including chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of NCF 800, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Datasheet for Steel Grades Specialsteel NCF 800

NCF 800 Standard Number:

ITEM	Standard Number	Descriptions
1	G 4902 (1991)	Corrosion-resisting and heat-resisting superalloy plates and sheets

NCF 800 Chemical composition(mass fraction)(wt.%)

Chemical	Min.(%)					Max.(%)				
C						0.10				
Si						1.00				
Mn						1.50				
P						0.03				
S						0.015				
Cr	19.00					23.00				
Ni	30.00					35.00				
Cu						0.75				
Al	0.15					0.60				
Ti	0.15					0.60				
Fe	remaining									
C	Si	Mn	P	S	Cr	Ni	Mo	V	Ta	
W	N	Cu	Co	Pb	B	Nb	Al	Ti	Other	

Corrosion-resisting and heat-resisting superalloy plates and sheets

NCF 800 Physical Properties

Tensile strength	115-234	σ_b /MPa
Yield Strength	23	$\sigma_{0.2} \geq$ /MPa
Elongation	65	$\delta_5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	Akv \geq /J
HBS	123-321	-
HRC	30	-

NCF 800 Mechanical Properties

Tensile strength	231-231	σ_b /MPa
Yield Strength	154	$\sigma_{0.2} \geq$ /MPa
Elongation	56	$\delta_5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	Akv \geq /J
HBS	235-268	-
HRC	30	-

NCF 800 Heat Treatment Regime

Annealing	Quenching	Tempering	Normalizing	Q & T
√	√	√	√	√

NCF 800 Range of products

Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Steel Bar	Round Bar, Flat Bar,	Φ8-1200mm*L	Forging, hot rolling and	Black, Rough Turning,

	Square Bar		cold rolling, Cast	Shot Blasting,
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot-Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-WASHED

We can produce Specialsteel the specifications follows: