

This page is mainly introduced the 1.4362 Datasheet, including chemical information,mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of 1.4362,such as it is commonly used in bars, sheet,plates, steel coils, steel pipes,forged and other materials application.

Datasheet for Steel Grades Specialsteel 1.4362

| 1.4362 Standard Number: | | | | | |
|-------------------------|-----------------------|--|--|--|--|
| ITEM | Standard Number | Descriptions | | | |
| 1 | DIN EN 10088-1 | Stainless steels - Part 1: List of stainless steels | | | |
| 2 | DIN EN 10088-2 | Stainless steels - Part 2: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for general purposes | | | |
| 3 | DIN EN 10088-3 | Stainless steels - Part 3: Technical delivery conditions for semi-finished products, bars, rods, wire, sections and bright products of corrosion resisting steels for general purposes | | | |
| 4 | DIN EN 10088-4 | Stainless steels - Part 4: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for construction purposes | | | |
| 5 | DIN EN 10028-7 | Flat products made of steels for pressure purposes - Part 7: Stainless steels | | | |
| 6 | DIN EN 10088-5 | Stainless steels - Part 5: Technical delivery conditions for bars, rods, wire, sections and bright products of corrosion resisting steels for construction purposes | | | |
| 7 | DIN EN 10216-5 (2004) | Seamless steel tubes for pressure purposes - Technical delivery conditions - Part 5: Stainless steel tubes | | | |
| 8 | DIN EN 10217-7 | Welded steel tubes for pressure purposes - Technical delivery conditions - Part 7: Stainless steel tubes | | | |
| 9 | DIN EN 10250-4 | Open die steel forgings for general engineering purposes - Part 4: Stainless steels | | | |
| 10 | DIN EN 10253-3 | Butt-welding pipe fittings - Part 3: Wrought austenitic and austenitic-ferritic (duplex) stainless steels without specific inspection requirements | | | |
| 11 | DIN EN 10253-4 | Butt-welding pipe fittings - Part 4: Wrought austenitic and austenitic-ferritic (duplex) stainless steels with specific inspection requirements | | | |
| 12 | DIN EN 10272 | Stainless steel bars for pressure purposes | | | |
| 13 | DIN EN 10296-2 (2005) | Welded circular steel tubes for mechanical and general engineering purposes - Technical delivery conditions - Part 2: Stainless steel | | | |
| 14 | DIN EN 10297-2 (2005) | Seamless circular steel tubes for mechanical and general engineering purposes - Technical delivery conditions - Part 2: Stainless steel | | | |
| 15 | SEW 400 | Stainless steels for rolled and forged products | | | |

| 1.4362 Chemical composition(mass fraction)(wt.%) | | | | | |
|--|---------|---------|--|--|--|
| Chemical | Min.(%) | Max.(%) | | | |
| С | | 0.030 | | | |

Steel Grades 1.4362 Chemical information, Mechanical properties

Physical properties, Mechanical properties, Heat treatment, and Micro structure

| Si | | | | | | | 1.00 | | |
|----|----|----|----|-------|----|----|------|-------|-------|
| Mn | | | | | | | 2.50 | | |
| Р | | | | | | | | 0.035 | |
| S | | | | 0.015 | | | | | |
| Cr | | | | 22.0 | | | 24.0 | | |
| | Мо | | | 0.10 | | | 0.60 | | |
| | Ni | | | 3.00 | | | 5.50 | | |
| N | | | | 0.05 | | | 0.20 | | |
| | Cu | | | 0.10 | | | 0.60 | | |
| С | Si | Mn | Р | S | Cr | Ni | Мо | V | Та |
| | | | | | | | | | |
| W | N | Cu | Co | Pb | В | Nb | Al | Ti | Other |
| | | | | | | | | | |

Stainless steels - Part 3: Technical delivery conditions for semi-finished products, bars, rods, wire, sections and bright products of corrosion resisting steels for general purposes

| 1.4362 Physical Properties | | | | | |
|----------------------------|---------|-------------|--|--|--|
| Tensile strength | 115-234 | σb/MPa | | | |
| Yield Strength | 23 | σ 0.2 ≥/MPa | | | |
| Elongation | 65 | δ5≥ (%) | | | |
| Ψ | - | ψ≥ (%) | | | |
| Akv | - | Akv≥/J | | | |
| HBS | 123-321 | - | | | |
| HRC | 30 | - | | | |

| 1.4362 Mechanical Properties | | | | | |
|------------------------------|---------|-------------|--|--|--|
| Tensile strength | 231-231 | σb/MPa | | | |
| Yield Strength | 154 | σ 0.2 ≥/MPa | | | |
| Elongation | 56 | δ5≥(%) | | | |
| Ψ | - | ψ≥(%) | | | |
| Akv | - | Akv≥/J | | | |
| HBS | 235-268 | - | | | |
| HRC | 30 | - | | | |

Steel Grades 1.4362 Chemical information, Mechanical properties

Physical properties, Mechanical properties, Heat treatment, and Micro structure

| 1.4362 Heat Treatment Regime | | | | | | | | |
|------------------------------|---|---|---|---|--|--|--|--|
| Annealing | Annealing Quenching Tempering Normalizing Q & T | | | | | | | |
| √ | √ | √ | √ | √ | | | | |

| 1.4362 Range of products | | | | | | | |
|--------------------------|---|-------------------------------|---|--|--|--|--|
| Product type | Products | Dimension | Processes | Deliver Status | | | |
| Plates / Sheets | Plates / Sheets | 0.08-200mm(T)*W*L | Forging, hot rolling and cold rolling | Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting | | | |
| Steel Bar | Round Bar, Flat Bar, Square Bar | Ф8-1200mm*L | Forging, hot rolling and cold rolling, Cast | Black, Rough Turning, Shot Blasting, | | | |
| Coil / Strip | Steel Coil /Steel Strip | 0.03-16.0x1200mm | Cold-Rolled & Hot- Rolled | Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting | | | |
| Pipes / Tubes | Seamless Pipes/Tubes, Welded Pipes/Tubes | OD:6-219mm x WT:0.5-20.0mm | Hot extrusion, Cold Drawn, Welded | Annealed, Solution and Aging, Q+T, ACID- WASHED | | | |

We can produce Specialsteel the specifications follows: