

This page is mainly introduced the X3CrNiMo13-4 Datasheet, including chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of X3CrNiMo13-4, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

Datasheet for Steel Grades Specialsteel X3CrNiMo13-4

X3CrNiMo13-4 Standard Number:

ITEM	Standard Number	Descriptions
1	BS EN 10028-7	Flat products made of steels for pressure purposes - Part 7: Stainless steels
2	BS EN 10088-1	Stainless steels - Part 1: List of stainless steels
3	BS EN 10088-2	Stainless steels - Part 2: Technical delivery conditions for sheet/plate and strip of corrosion resisting steels for general purposes
4	BS EN 10088-3	Stainless steels - Part 3: Technical delivery conditions for semi-finished products, bars, rods, wire, sections and bright products of corrosion resisting steels for general purposes
5	BS EN 10222-5	Steel forgings for pressure purposes - Part 5: Martensitic, austenitic and austenitic-ferritic stainless steels
6	BS EN 10250-4	Open die steel forgings for general engineering purposes - Part 4: Stainless steels
7	BS EN 10272	Stainless steel bars for pressure purposes

X3CrNiMo13-4 Chemical composition(mass fraction)(wt.%)

Chemical		Min.(%)		Max.(%)					
C				0.05					
Si				0.70					
Mn				1.50					
P				0.04					
S				0.015					
Cr		12.00		14.00					
Ni		3.50		4.50					
Mo		0.30		0.70					
N		0.020							
C	Si	Mn	P	S	Cr	Ni	Mo	V	Ta
W	N	Cu	Co	Pb	B	Nb	Al	Ti	Other

--	--	--	--	--	--	--	--	--	--

Stainless steel bars for pressure purposes

X3CrNiMo13-4 Physical Properties

Tensile strength	115-234	σ_b /MPa
Yield Strength	23	$\sigma_{0.2} \geq$ /MPa
Elongation	65	$\delta 5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	Akv \geq J
HBS	123-321	-
HRC	30	-

X3CrNiMo13-4 Mechanical Properties

Tensile strength	231-231	σ_b /MPa
Yield Strength	154	$\sigma_{0.2} \geq$ /MPa
Elongation	56	$\delta 5 \geq$ (%)
ψ	-	$\psi \geq$ (%)
Akv	-	Akv \geq J
HBS	235-268	-
HRC	30	-

X3CrNiMo13-4 Heat Treatment Regime

Annealing	Quenching	Tempering	Normalizing	Q & T
√	√	√	√	√

X3CrNiMo13-4 Range of products

Product type	Products	Dimension	Processes	Deliver Status
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting

Steel Bar	Round Bar, Flat Bar, Square Bar	Φ8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot-Rolled	Annealed, Solution and Aging, Q+T, ACID-WASHED, Shot Blasting
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID-WASHED

We can produce Specialsteel the specifications follows: