

This page is mainly introduced the X33Cr13 Datasheet, including chemical information, mechanical properties, physical properties, mechanical properties, heat treatment, and Micro structure, etc. It also contains the use of X33Cr13, such as it is commonly used in bars, sheet, plates, steel coils, steel pipes, forged and other materials application.

## Datasheet for Steel Grades Tool Steel And Hard Alloy X33Cr13

X33Cr13 Standard Number:						
ITEM	ITEM Standard Number Descriptions					

X33Cr13 Chemical composition(mass fraction)(wt.%)									
Chemical Min.(%) Max.(%)									
С	Si	Mn	Р	S	Cr	Ni	Мо	V	Та
0.28-0.38	≤1.00	≤1.00			12.0-14.0				
W	N	Cu	Со	Pb	В	Nb	Al	Ti	Other

X33Cr13 Physical Properties					
Tensile strength 115-234 σb/MPa					
Yield Strength	23	σ 0.2 ≥/MPa			
Elongation	65	δ5≥ (%)			
ψ	-	ψ≥ (%)			
Ακν	-	Akv≥/J			
HBS	123-321	-			
HRC	30	-			

X33Cr13 Mechanical Properties					
Tensile strength	231-231	σb/MPa			
Yield Strength	154	σ 0.2 ≥/MPa			



Elongation	56	δ5≥(%)
Ψ	-	ψ≥(%)
Akv	-	Akv≥/J
HBS	235-268	-
HRC	30	-

X33Cr13 Heat Treatment Regime							
Annealing	Annealing Quenching Tempering Normalizing Q & T						
	$\checkmark$	$\checkmark$	$\checkmark$	$\checkmark$			

X33Cr13 Range of products							
Product type	Products	Dimension	Processes	Deliver Status			
Plates / Sheets	Plates / Sheets	0.08-200mm(T)*W*L	Forging, hot rolling and cold rolling	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting			
Steel Bar	Round Bar, Flat Bar, Square Bar	Ф8-1200mm*L	Forging, hot rolling and cold rolling, Cast	Black, Rough Turning, Shot Blasting,			
Coil / Strip	Steel Coil /Steel Strip	0.03-16.0x1200mm	Cold-Rolled & Hot- Rolled	Annealed, Solution and Aging, Q+T, ACID- WASHED, Shot Blasting			
Pipes / Tubes	Seamless Pipes/Tubes, Welded Pipes/Tubes	OD:6-219mm x WT:0.5-20.0mm	Hot extrusion, Cold Drawn, Welded	Annealed, Solution and Aging, Q+T, ACID- WASHED			

## We can produce Tool Steel And Hard Alloy the specifications follows: